

 **novawood**[®]

INTERIORS & EXTERIORS

novathermowood[®]

EXTERIOR PRODUCTS QUALITY DEFINITIONS



Novathermowood Pine

- Thermowood process is carried out in 212°C according to principles of International Thermowood Association and European Norms DIN CEN/TS 15679:2008-03/ .
- novathermowood Pine Decking and Cladding products are with wing-knots and are sound knotted.
- The raw materials used for the Thermowood Process are being obtained from 2 E X cut Logs originating from Finland.
- Splits on knots may occur after the Thermowood process due to High heat treatment but this will not effect the durability of the product.
- Knots, moulding impacts, inability to recover the measures can be found at the back side of the boards (invisible part) of the decking and cladding products.
- novathermowood Pine products are one side usable products. For two face clear products please talk to our sales team.
- Dimensional Tolerance:
 - Length: +/- 2 mm (DIN EN 14519)
 - Width: +/- 1 mm (DIN EN 4074-5)
 - Thickness: +/-1 mm (DIN EN 4074-5)
- novathermowood Pine products are manufactured according to DIN EN 335-2 ve DIN EN 350-2 and classified as Durability Class 2.
- novathermowood Pine products are light brown colour but as being a natural resource colour differences may occur.
- novathermowood Pine products are provided in 20-5 20 mm lengths.



novathermowood Iroko

- The Thermowood process for Iroko is carried out in 200°C according to principles of International Thermowood Association and European Norms DIN CEN/TS 15679:2008-03/ .
- Thermowood Iroko Decking and Cladding products are free of Sapwood.
- Raw materials are originating from Congo and Cameroon regions.
- Knots, moulding impacts, inability to recover the measures can be found at the back side of the boards (invisible part) of the decking and cladding products. novathermowood Iroko products are one side usable products.
- novathermowood Iroko products are one side usable products.
- Dimensional Tolerance:
 - Length: +/- 2 mm (DIN EN 14519)
 - Width: +/- 1 mm (DIN EN 4074-5)
 - Thickness: +/-1 mm (DIN EN 4074)
- novathermowood Iroko products are made according to DIN EN 335-2 ve DIN EN 350-2 and classified as Durability Class 1.
- novathermowood Iroko products come in honey colour but as being a natural resource colour differences between boards may occur.
- novathermowood Iroko products are provided in 1000-3000 mm lengths.

